


# DIAMCALC STANDARD REPORT

# Polished Brilliant

## General information

Model Sample Helium Brilliant  
 Expert name Sample Expert Name  
 Report date 06.09.2006  
 Real weight, ct 0.37  
 Calculated weight, ct 0.37, 0.3764  
 Total height 2.722 mm, 56.96 %  
 Total height quality N/A  
 Appraiser title AGS\_2005  
 Overall cut quality 3  
 Overall symmetry quality PR



## Main parameters

Parameter		Avg	Min	Max	Dev	Cut	Sym
Diameter	mm	4.778	4.765	4.792	0.57 %	N/A	EX
Crown angle	°	32.25	31.11	32.55	1.44	N/A	VG
Crown height	%	11.38	10.61	12.35	1.75	N/A	VG
Pavilion angle	°	40.68	39.68	41.53	1.86	N/A	VG
Pavilion depth	%	42.72	41.72	43.77	2.05	N/A	GD
Lower girdle facets angle	°	41.57	40.59	42.49	1.90	-	VG
Upper girdle facets angle	°	39.95	39.01	41.04	2.03	-	GD
Star facets angle	°	18.74	17.50	19.77	2.27	-	GD
Star : Upper ratio	%	58.29 :	53.81 :	62.79:	8.98	-	PR
Table	%	64.03	63.82	64.12	0.29	N/A	EX
Culet	%	0.57	0.39	0.68	0.28	0	EX
Twist	°	1.49	0.17	3.62	3.45	-	VG
Girdle thickness: Bezel	%	2.84	2.41	3.40	0.98	0	EX
Girdle thickness: Bone	%	3.31	3.02	3.71	0.69		EX
Girdle thickness: Valley	%	1.55	1.22	1.98	0.75	0	EX

	C-Height	P-Depth	Table	Culet	G-Bezel	G-Bone	G-Value
Average value, mm	0.544	2.041	3.059	0.027	0.136	0.158	0.074